

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) Publication number:

**0 506 033 A1**

(12)

## EUROPEAN PATENT APPLICATION

(21) Application number: **92105166.0**

(51) Int. Cl.<sup>5</sup>: **C08K 3/36, C08L 67/02,  
C08J 5/18**

(22) Date of filing: **25.03.92**

(30) Priority: **28.03.91 JP 64870/91**

(43) Date of publication of application:  
**30.09.92 Bulletin 92/40**

(84) Designated Contracting States:  
**DE FR GB IT LU NL**

(71) Applicant: **DIAFOIL HOECHST CO., LTD.**  
**3-2, Marunouchi 2-chome, Chiyoda-ku**  
**Tokyo(JP)**

(72) Inventor: **Fujimoto, Masahiko, c/o Daiahoiru**  
**Hekisuto K. K.**  
**Chuokenkyusho-nai, 1000 Kamoshida-cho,**  
**Midori-ku**  
**Yokohama-shi(JP)**  
Inventor: **Endo, Kazuo, c/o Daiahoiru Hekisuto**  
**K. K.**  
**Chuokenkyusho-nai, 1000 Kamoshida-cho,**  
**Midori-ku**  
**Yokohama-shi(JP)**

(74) Representative: **TER MEER - MÜLLER -**  
**STEINMEISTER & PARTNER**  
**Mauerkircherstrasse 45**  
**W-8000 München 80(DE)**

(54) **Polyester film.**

(57) A polyester film having uniform surface and excellent running property and transparency is disclosed. Said polyester film is characterized by containing 0.01-5 wt% of porous precipitated silica particles which are coagulates of primary particles having an average particle diameter of 0.01-0.1  $\mu\text{m}$  and have a pore volume of 0.05-0.5 ml/g, a specific surface area of 30-150 m<sup>2</sup>/g and an average particle diameter of 0.1-0.5  $\mu\text{m}$ .

EP 0 506 033 A1

The present invention relates to a polyester film which contains silica particles having specific physical properties and has excellent surface and running properties.

[Background of the Invention]

Polyester films typified by polyethylene terephthalate have excellent physical and chemical properties and thus are used in various fields such as graphic art, display, wrapping, base film for magnetic recording media, dielectric materials for condenser, etc.

In order to manufacture polyester films having excellent properties, it is essential to impart good running property to the film in the aspects of passing through the manufacturing steps, finishing steps after the film is coated by application or vapor deposition or handling of the product per se. Polyester films, however, are not entirely satisfactory in this respect. The deficiency is, in most cases, manifested by friction and abrasion caused when the film slides in contact with apparatus parts at high speed.

It is well known to properly roughen the surface of films in order to improve their running property and abrasion resistance. In order to achieve this object, fine particles are incorporated in the polyester. Although this is practically employed in industry to some degree, it is not always successful in providing the desired properties.

For instance, when the so-called precipitated particles, which are formed from the catalyst residue during the preparation of polyester, are employed, control of the amount of the particles, particle diameter, prevention of formation of coarse particles, etc. are difficult. Such particles are easily broken when the film is drawn (stretched) and do not bring about good running property and abrasion resistance. Also recycled use of such films is difficult.

Another means is to add inorganic particles of calcium carbonate, titanium dioxide, calcium phosphate, etc., which are inert to polyester. These particles are not subject to breakdown or deformation during the drawing and form rather steep protrusions and, therefore, bring about good running property. However, these particles have poor affinity with polyester and void spaces are formed around the particles when the film is drawn, which markedly degrades the transparency of the film. Also, these particles easily come off from the film surface and become white dust.

It is known to use silica particles which have relatively good affinity with polyester (Japanese Laying-Open Patent Publication No.37-12150 and 53-453696, for instance). As described in Japanese Laying Open Patent Publication No. Sho 43-23960, however, the dispersibility of silica particles in polyester is very poor and, therefore, they coagulate during the synthesis of polyester causing formation of coarse protrusions on the surface of the resulting film and degrading the transparency of the film. Further there is some difficulty that silica reduces the polymerization rate and degrades the thermal stability of the resulting film. The reason for this is not entirely clear but it is surmised that silanol groups existing on the surface of silica particles might react with the metal compound as the polymerization catalyst and the metal compound might be partially trapped by the silica.

We conducted intensive research in order to obtain a film provided with excellent surface properties, running property and other characteristics required for a base film and found that such a film can be obtained by incorporating silica particles which have specific physical properties and completed this invention.

The gist of the present invention resides in a polyester film characterized by containing 0.01-5 wt%, preferably 0.1-3 wt%, of porous precipitated silica particles which are coagulated particles of primary particles each having an average particle diameter of 0.01-0.1  $\mu\text{m}$ , preferably 0.03-0.08  $\mu\text{m}$ , and have a pore volume of 0.05-0.5 ml/g, preferably 0.07-0.3 ml/g, a specific surface area of 30-150  $\text{m}^2/\text{g}$ , preferably 50-130  $\text{m}^2/\text{g}$  and an average particle diameter of 0.1-5  $\mu\text{m}$ , preferably 0.2-3  $\mu\text{m}$ .

The invention will be described below in details.

The term "polyester" as used in the present invention means polyester which is prepared from an aromatic dicarboxylic acid such as terephthalic acid, 2,6-naphthalenedicarboxylic acid, etc. or an ester thereof and a glycol and may contain a third component. Specific examples the dicarboxylic acid are isophthalic acid, terephthalic acid, 2,6-naphthalenedicarboxylic, adipic acid and sebacic acid, etc. Specific examples of the glycol component are ethylene glycol, diethylene glycol, propylene glycol, butanediol, 1,4-cyclohexanedimethanol, neopentylglycol, etc. or mixtures thereof. The polyester used in the present invention preferably contains not less than 80 % of repeating units of ethylene terephthalate or ethylene-2,6-naphthalate units.

In the present invention, the "polyester film" means a polyester film which is prepared from the above-described polyester and oriented at least in one direction. Such polyester film can be prepared by a method known per se. For instance, the film can be prepared by melt-extruding the polyester into a sheet at

270-320 °C, cooling to 40-80 °C to solidify the sheet, longitudinally and transversally stretching the thus prepared amorphous sheet simultaneously or sequentially by a factor of 4-20 in area and finally heat-treating it at 160-250 °C (the method disclosed in Japanese Patent Publication No. Sho 30-5639 for instance). The longitudinal and transversal, i.e., biaxial stretching can be effected in one step or in a plurality of steps. In the case of multiple step stretching, a heat treatment step for orientation relaxation can be interposed. After the biaxial stretching and before the heat treatment, an additional stretching step or steps can be interposed. This additional stretching can be effected in one direction or both directions.

The present invention is characterized by using, as particles to be incorporated in the polyester film, specific silica particles, which satisfy specific conditions with respect to the average particle diameter of the primary particles which constitute the silica particles, specific surface areas and the pore volume of the coagulated particles,

The term "primary particle" as referred to in the present specification means the smallest silica particle unit which can be discriminated as one particle. In the present invention, particles comprising a plurality of primary particles which are partially chemically bonded to each other are used.

The above-described silica particles can be prepared by a so-called wet process, a reaction of sodium silicate and a mineral acid, for instance, to produce particles principally comprising silica. The conditions of the particles can be controlled by adjusting reaction temperature, conditions of ions that are present, etc.

Silica particles obtained by a wet process are porous silica particles which usually have a specific surface area of 300-700 m<sup>2</sup>/g (by the BET method) and a pore volume of 0.7-2 ml/g and contain many silanol groups on the surface and in the interior. When such porous silica particles are incorporated in polyester, the particles are more or less deformed as the film is prepared by drawing, that is, they well follow the drawing and thus exhibit good affinity to polyester film. The resulting film has excellent abrasion resistance.

Generally, particles are incorporated in polyester by adding a slurry of the particles in the reaction mixture during the synthesis thereof. If ordinary porous silica particles are used, the particles are often triturated into smaller particles and the resulting fine particles again coagulate, thus irregularity in the particle size is caused during the preparation of the slurry.

When silica particles contain many silanol groups, they are apt to coagulate by the interaction of the silanol groups. When silica particles containing many silanol groups are added to the reaction mixture, the polymerization reaction is retarded as mentioned above.

The primary particles constituting the porous precipitated silica particles used in the present invention should have an average particle diameter of 0.01-0.1 µm. The particles having a particle diameter of less than 0.01 µm are apt to be broken down to ultrafine particles, which coagulate again. The particles having an average particle diameter of more than 0.1 µm have poor porosity and thus poor affinity to polyester.

The porous precipitated silica particles used in the present invention should have a pore volume of 0.05-0.5 ml/g and a specific surface area of 30-150 m<sup>2</sup>/g. Particles having a pore volume smaller than 0.05 ml/g or a specific surface area of smaller than 30 m<sup>2</sup>/g have poor porosity. Particles having a pore volumes larger than 0.5 ml/g or a specific surface area larger than 150 m<sup>2</sup>/g have a large number of silanol groups.

The porous precipitated silica particles to be used in the present invention should have an average particle diameter of 0.1-5 µm, preferably 0.2-3 µm. With particles having an average particle diameter of smaller than 0.1 µm, the resulting film is poor in the running property and abrasion resistance. With the particles having an average particle diameter of larger than 5 µm, the resulting film has too high a surface roughness.

The content of the porous precipitated silica particles in the polyester film should be 0.01-5 wt%, preferably 0.1-1 wt%. When the content is less than 0.01 wt%, the resulting film is insufficient in running property and abrasion resistance. When the content is larger than 5 wt%, the resulting film has too high a surface roughness.

The manner of incorporating the silica particles in polyester in the present invention is not specifically defined but can be effected by any known method. However, it is preferred to add them in the form of a slurry, a dispersion in ethylene glycol for instance, at any stage in the preparation of the polyester, preferably after the esterification or transesterification and before the polymerization.

The slurry can be prepared by any known technique. For instance, the particles can be dispersed in ethylene glycol by means of a high speed mixer provided with a plurality of shearing blades arranged in parallel with the rotation of agitating wings, a homomixer, an ultrasonic disperser, etc.

The obtained slurry is preferably filtered with a screen of 1000 mesh or smaller in order to remove coarse particles and undispersed coagulated particles.

The surface property, running property and abrasion resistance of polyester film can be highly improved by incorporating silica particles having specific properties in the polyester. The resulting film is

especially suitable as base film for electrical appliances such as magnetic recording media represented by magnetic tape and flexible magnetic discs as well as condensers. The application of the film is not limited thereto but the film is useful as a base film for photographic printing plate and packaging, etc.

Other particles, e.g., those of kaolin, talc, calcium carbonate, aluminum oxide, particles of cross-linked high polymer, etc., can be used in addition to the above described silica particles as desired within the gist of the invention.

The invention will now be described specifically in detail by way of working examples. However, the invention is not limited to these examples but by the scope of the gist of the invention. The definitions and methods of measurement of the properties and characteristics referred to in the following examples are as follows: The term "parts" in the examples means "parts by weight"

#### (1) Particle diameter

The average particle diameter of silica particles means the diameter at 50 % of the integral volume percentage in the equivalent sphere distribution measured with a centrifugal sedimentation particle distribution measurement apparatus (SA-CP3) manufactured by Shimadzu Seisakusho.

The particle diameter of the primary particles was measured by graphic processing of electron microscope images.

#### (2) Pore volume and specific surface area

Pore volume and specific surface area were measured by nitrogen adsorption-desorption method using a full-automatic surface area measurement apparatus (manufactured by Carlo Erba, S.p.A.).

#### (3) Intrinsic viscosity

Intrinsic viscosity of polymer was measured at 30.0 °C using a solution of 1 g of polymer in 100 ml of phenol-tetrachloroethane mixture (50/50 by weight).

#### (4) Running property

Two strips of film 15 mm in width and 150 mm in length were placed one over another on a smooth glass plate, a rubber plate was placed thereon so as to give a contact pressure of 2 g/cm<sup>2</sup> and one strip was slid over the other at the rate of 20 mm/min. The friction coefficient was measured and the friction coefficient at the point the film slid by 5 mm was taken as the dynamic friction coefficient. This was made an index of running property.

The measurement was carried out at 23±1 °C under the RH of 50±5 %.

#### (5) Abrasion resistance

The abrasion resistance of film was evaluated by the amount of produced white powder when the film was slid over a fixed pin. A film (tape) was contacted with the surface of a fixed hard chromium-plated pin having a diameter of 6 mm over an angle of 135 ° and slid over 1000 m at the rate of 13 m/min with a tension of about 200 g. The amount of the produced white powder adhering the pin was visually observed and rated as follows.

- A: No powder adhering
- B: A slight amount of powder adhering
- C: A little amount (larger than B) of powder adhering
- D: A large amount of powder adhering

#### (6) Number of coarse protrusions

A 10 mg (polymer) sample was precisely weighed and placed between two 18x18 mm cover glass plates and hot-pressed at 280-290 °C so as to form a film piece having a diameter of 10 mm. This film was observed under a phase difference microscope (x100) and the number of particles having a diameter of 10 μm or larger was counted. The value was taken as the number of coarse protrusions.

#### Example 1

## (Preparation of slurry)

Ten (10) parts of precipitated silica particles, which were each a coagulate of primary particles having an average particle diameter of  $0.05\ \mu\text{m}$  and had an average particle diameter of  $0.50\ \mu\text{m}$ , a pore volume of  $0.09\ \text{ml/g}$  and a specific surface area of  $70\ \text{m}^2/\text{g}$ , were added to 90 parts of ethylene glycol and dispersed by means of a homomixer ("TK Homomixer" manufactured by Tokushu Kika Kogyo Kabushiki Kaisha) at 10000 rpm for 60 min. The resulting dispersion was filtered with a 1000 mesh wire screen. Thus a silica particle ethylene glycol slurry was obtained.

## 10 (Preparation of polyester)

In a reactor, 100 parts of dimethyl terephthalate, 60 parts of ethylene glycol and 0.09 parts of magnesium acetate tetrahydrate were placed and heated. Transesterification was allowed to proceed by heating and distilling off produced methanol as the temperature rose. After 4 hours, the temperature reached  $230\ ^\circ\text{C}$  and the transesterification was substantially completed. Then 3 parts of the above-described slurry was added to the reaction mixture and further 0.04 parts of ethyl acid phosphate and 0.04 parts of antimony trioxide were added. Thus polycondensation reaction was allowed to proceed. After 4 hours and 15 minutes, polyethylene terephthalate having an intrinsic viscosity of 0.660 was obtained.

The obtained polyester was dried and melt-extruded at  $290\ ^\circ\text{C}$  into an amorphous polyester sheet, which was longitudinally stretched at  $90\ ^\circ\text{C}$  by a factor of 3.5, transversally stretched at  $110\ ^\circ\text{C}$  by a factor of 3.7 and finally heat-treated at  $210\ ^\circ\text{C}$  for 3 seconds. Thus a  $15\ \mu\text{m}$  thick film was obtained and the characteristics were evaluated.

## Example 2

Using precipitated silica particles, which were each a coagulate of primary particles having an average particle diameter of  $0.02\ \mu\text{m}$  and had an average particle diameter of  $0.50\ \mu\text{m}$ , a pore volume of  $0.15\ \text{ml/g}$  and a specific surface area of  $133\ \text{m}^2/\text{g}$ , the polycondensation reaction was carried out in the same manner as in Example 1. After 4 hours and 20 minutes, polyethylene terephthalate having an intrinsic viscosity of 0.661 was obtained. A film was obtained in the same manner as in Example 1 and the characteristics thereof were evaluated.

## Example 3

Using precipitated silica particles, which were each a coagulate of primary particles having an average particle diameter of  $0.07\ \mu\text{m}$  and had an average particle diameter of  $1.20\ \mu\text{m}$ , a pore volume of  $0.25\ \text{ml/g}$  and a specific surface area of  $90\ \text{m}^2/\text{g}$ , the polycondensation reaction was carried out in the same manner as in Example 1. After 4 hours and 10 minutes, polyethylene terephthalate having an intrinsic viscosity of 0.664 was obtained.

A film was obtained in the same manner as in Example 1 and the characteristics thereof were evaluated.

## Comparative Example 1

Using precipitated silica particles, which were each a coagulate of primary particles having an average particle diameter of  $0.005\ \mu\text{m}$  and have an average particle diameter of  $0.50\ \mu\text{m}$ , a pore volume of  $0.95\ \text{ml/g}$  and a specific surface area of  $210\ \text{m}^2/\text{g}$ , the polycondensation reaction was carried out in the same manner as in Example 1. After 5 hours and 10 minutes, polyethylene terephthalate having an intrinsic viscosity of 0.651 was obtained. A film was obtained in the same manner as in Example 1 and the characteristics thereof were evaluated.

## Comparative Example 2

Using precipitated silica particles, which were each a coagulate of primary particles having an average particle diameter of  $0.3\ \mu\text{m}$  and had an average particle diameter of  $1.20\ \mu\text{m}$ , a pore volume of  $0.04\ \text{ml/g}$  and a specific surface area of  $210\ \text{m}^2/\text{g}$ , the polycondensation reaction was carried out in the same manner as in Example 1. After 4 hours and 10 minutes, polyethylene terephthalate having a limiting viscosity of 0.651 was obtained. A film was obtained in the same manner as in Example 1 and the characteristics thereof

were evaluated.

Comparative Example 3

5 Using precipitated silica particles, which were each a coagulate of primary particles having an average  
particle diameter of  $0.05\ \mu\text{m}$  and had an average particle diameter of  $0.5\ \mu\text{m}$ , a pore volume of  $0.09\ \text{ml/g}$   
and a specific surface area of  $70\ \text{m}^2/\text{g}$ , the polycondensation reaction was carried out in the same manner  
as in Example 1. After 5 hours and 40 minutes, polyethylene terephthalate having an intrinsic viscosity of  
0.651 was obtained. A film was obtained in the same manner as in Example 1 and the characteristics  
10 thereof were evaluated.

15

20

25

30

35

40

45

50

55

Table 1

	Silica Particles					Polymer Characteristics		Film Characteristics		
	Primary Particles ( $\mu m$ ) Part. diam.	Pore Vol. ( $ml/g$ )	Spec. Area ( $m^2/g$ )	Average Diameter ( $\mu m$ )	Content (%)	Polymeriz'n Time	Intrinsic Vis'y	Running Prop.	Abrasion Resistance	No. of Coarse protrusion
Ex. 1	0.05	0.09	70	0.50	0.3	4 hr. 15 min.	0.660	0.36	A	3
Ex. 2	0.02	0.15	133	0.50	0.3	4 hr. 20 min.	0.661	0.32	A	5
Ex. 3	0.07	0.25	90	1.20	0.3	4 hr. 10 min.	0.664	0.32	A	5
Comp. Ex. 1	0.005	0.95	210	0.50	0.3	5 hr. 10 min.	0.651	0.44	A	35
Comp. Ex. 2	0.3	0.04	25	1.20	0.3	4 hr. 10 min.	0.665	0.40	C	8
Comp. Ex. 3	0.05	0.09	70	0.50	6.0	6 hr. 40 min.	0.651	0.22	B	74

The film of the present invention has a uniform surface as well as excellent running property and transparency, thus is applicable to various uses and industrially very valuable.

#### Claims

1. A polyester film characterized by containing 0.01-5 wt% of porous precipitated silica particles which are coagulates of primary particles having an average particle diameter of 0.01-0.1  $\mu\text{m}$ , a pore volume of 0.05-0.5 ml/g, a specific surface area of 30-150  $\text{m}^2/\text{g}$  and an average particle diameter of 0.1-5  $\mu\text{m}$ .
- 5 2. A polyester film as claimed in claim 1, wherein the content of the silica particle is 0.1-1 wt%.
3. A polyester film as claimed in claim 1, wherein the particle diameter of the silica particles is 0.2-1  $\mu\text{m}$ .
- 10 4. A polyester film as claimed in claim 1, wherein the pore volume of the silica particles is 0.07-0.3 ml/g.
5. A polyester film as claimed in claim 1, wherein the specific surface area of the silica particles is 50-130  $\text{m}^2/\text{g}$ .
- 15 6. A polyester film as claimed in claim 1, wherein the particle diameter of the primary particles of the silica particles 0.03-0.08  $\mu\text{m}$ .



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number

EP 92 10 5166

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	EP-A-0 257 611 (OIAFOIL COMPANY, LIMITED) * comparative example B-1 * * table 2 *	1-3,6	C08K3/36 C08L67/02 C08J5/18
P,X	EP-A-0 423 402 (TEIJIN LIMITED) 24 April 1991 * comparative example 7 * * page 3, line 38 - page 4, line 37; claims 1,2,4,5,7; examples *	1-3,6	
A	US-A-4 497 918 (S.K. WASON) * column 4, line 50 - line 63; claims 1,2,4,7; examples 1A-1C *	1-3,5	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			C08K C08J
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 02 JULY 1992	Examiner FUHR C. K. B.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons * : member of the same patent family, corresponding document	